

# EUROPEAN PATENT OFFICE

## Patent Abstracts of Japan

PUBLICATION NUMBER : 03226247  
PUBLICATION DATE : 07-10-91

APPLICATION DATE : 30-01-90  
APPLICATION NUMBER : 02021673

APPLICANT : MITSUBISHI ELECTRIC CORP;

INVENTOR : MURAKAMI SADATOSHI;

INT.CL. : H02K 13/00 H01R 39/04

TITLE : COMMUTATOR FOR FUEL PUMP OF MOTORCAR

ABSTRACT : PURPOSE: To increase resistance to mechanical and electrical abrasion and improve the electric conductivity of the title commutator by employing a dispersion-type reinforced copper alloy for the commutator of a motor for an automotive fuel pump.

CONSTITUTION: The commutator of a motor for an automotive fuel pump is formed of an alumina dispersion-type reinforced copper alloy. The alumina dispersion-type reinforced copper alloy, containing 1.0weight% of  $Al_2O_3$ , is employed to effect the operation test of the same and the reduction of the amount of abrasion of about 80% is confirmed compared with the material of the commutator so far. The physical property i of the dispersion-type reinforced copper alloy is prominent in a hardness and a tensile strength compared with the material used so far. The deterioration of mechanical properties at a high temperature is small compared with the material so far. When the content of alumina is less than 0.1weight% of  $Al_2O_3$ , sufficient hardness and tensile strength can not be obtained but when it is more than 0.1weight%, the deterioration of electric conductivity is large and, therefore, the dispersion-type reinforced copper alloy having the composition specified above is optimum for the material of the commutator.

COPYRIGHT: (C)1991,JPO&Japio